



**TECHNICAL DATA
ORCHESTRA**

Date of review: 01/03/2006

CHARACTERISTICS	RESULTS		STANDARDS
	Warp	Weft	
WEAVE	Canvas		ISO 7211-1
MATERIAL	100% solution dyed acrylic Sunacryl		
YARNS PER CM	30	15	NF EN 1049-2
YARN COUNT	Nm 34/2	Nm 34/2	
FINISH	Cleangard special anti-staining and waterproof treatment for awnings		
WIDTH	120 cm +/- 0,5 cm		EN 1773
WEIGHT	300 gr/m ² +/- 7%		NF G 07150
LIGHT FASTNESS	7 - 8 / 8		NF EN ISO 105 B02
WEATHER FASTNESS	7 - 8 / 8		NF EN ISO 105 B04
WATER COLUMN	350 mm minimum		ISO 811
SPRAY TEST	5 / 5		ISO 4920
TENSILE STRENGTH	145 daN	90 daN	NF EN ISO 13934-1
TEAR STRENGTH	4,3 daN	2,3 daN	NF EN ISO 13937-1
STIFFNESS	1250 mN	880 mN	ISO 24 93
RECOMMENDED USES	Awnings of all sizes		
WARRANTY	5 years		

Complies with the EN 13561 standard

Those values are given for your information and correspond to the standard of production at the time of review of this sheet.